

BLC

980 - 1050 °C



Very white paste of great plasticity. Excellent drying behavior, also with glazes and underglazes . Ideal for turning, press, modeling...

Technical data sheet

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracci3n
22%	3,75%	1020°C	16,71%	19,00%	0,30%

Thermal coefficient

78.7x10⁻⁷°C⁻¹ (48.1°C-500°C)