

## FP CH 0-0,5 mm

980 - 1050 °C



Red earthenware body fine grog 0-0,5 mm  
 Excelent drying behavior. Perfect glaze and underglaze behavior.  
 Perfect for the artistic pottery, decorative, garden pots and sculpture.  
 Very plastic and easy to work.  
 Ideal for modelling

### Technical data sheet

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracci3n
22%	4,50%	1000°C	12,79%	12,76%	0,80%

### Thermal coefficient

72.2x10<sup>-7</sup>°C<sup>-1</sup> (48.1-500°C)