

**FP CH 0-1,5 mm****980 - 1050 °C**

Red earthenware body fine grog 1-0,5 mm  
Excelent drying behavior. Perfect glaze and underglaze behavior.  
Perfect for the artistic pottery, decorative, garden pots and sculpture.  
Very plastic and easy to work.  
Ideal for modelling

***Technical data sheet***

| Drying   |           |        | Firing    |                  |             |
|----------|-----------|--------|-----------|------------------|-------------|
| Humidity | Shrinkage | °C     | l. weight | Water Absorption | Contracci3n |
| 22%      | 5,5-6%    | 1020°C | 8,60%     | 12,76%           | 0,55%       |

***Thermal coefficient***74.1x10<sup>-7</sup>°C<sup>-1</sup> (48.1-500°C)