

GBCH 0-0,5 mm**1280 - 1300 °C**

White refractory stoneware high fire grogged 0-0,5 mm.
Nice texture. Excellent for lathe, modeling and raku.
Perfect for professionals and amateurs.

Technical data sheet

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	6,00%	1280°C		3,00%	4,00%

Thermal coefficient55.8x10⁻⁷°C⁻¹ (25-500°C)