

GBL**1280 - 1300 °C**

White stoneware with a smooth texture. Nice texture. Excellent for the lathe and tableware.
Perfect for professionals and amateurs.

Technical data sheet

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	6,00%	1280°C	6,60%	0,50%	9,00%

Thermal coefficient**52.5x10⁻⁷°C⁻¹ (25-500°C)**