

GSM CH 0-0,2 mm**1250 - 1260 °C**

Black stoneware high fire grogged 0-0,2 mm. Nice Texture. Excellent for the lathe and modeling. Perfect for professionals and amateurs

Technical data sheet

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	7,00%	1280		8,50%	7,00%

Thermal coefficient

51.1x10⁻⁷°C⁻¹ (25-500°C)