

**GSM CH 0-0,5 mm****1240 - 1260 °C**

Black stoneware high fire grogged 0-0,5 mm. Nice Texture. Excellent for the lathe and modeling. Perfect for professionals and amateurs

### *Technical data sheet*

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	7,00%	1250°C		8,50%	4,00%

### *Thermal coefficient*

55.7x10<sup>-7</sup>°C<sup>-1</sup> (25-500°C)