

REFRAC

950 - 980 °C



Ferruginous paste with low coefficient of expansion. Perfect for casseroles, baking trays and tajins. Smooth texture, special for direct flame.

Technical data sheet

Drying			Firing		
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracci3n
22%	8,00%	950	5,42%	12,10%	1,20%

Thermal coefficient

40.0x10⁻⁷°C⁻¹ (25-500°C)