

FSN**1020 - 1080 °C**

Black clay.
Excellent drying behavior glazes and underglazes (slipware). Intended for artistic, decorative, and table ceramics. High plasticity, shapable and easy to work with. Ideal for turning and modeling.

Technical data sheet

| Drying | | Firing | | | |
|----------|-----------|--------|-----------|------------------|-------------|
| Humidity | Shrinkage | °C | l. weight | Water Absorption | Contracción |
| 25% | 6,00% | 1020 | 7,00% | 8,90% | 2,30% |

Thermal coefficient