

BLC CH 0-0,5 mm**980 - 1050 °C**

White earthenware clay with grog 0-0,5 mm.
Excellent drying behavior, also with glazes and underglazes. Ideal for turning,
press, modeling

Technical data sheet

Drying			Firing		
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	4,50%	1020°C	16,71%	15,09%	3,00%

Thermal coefficient**C77,0x10⁻⁷°C⁻¹ (48.1-500°C)**