

BLC

980 - 1050 °C



Very white paste of great plasticity. Excellent drying behavior, also with glazes and underglazes. Ideal for turning, press, modeling...

Technical data sheet

Drying			Firing		
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	3,75%	1020°C	16,71%	19,00%	0,30%

Thermal coefficient

78.7x10⁻⁷°C⁻¹ (48.1°C-500°C)

Chemical composition

SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	CaO	MgO	NaO	K ₂ O	P ₂ O ₅	PF 1000°C
52,28%	15,22%	0,74%	0,48%	8,72%	4,56%	0,07%	2,74%	19,00%	15,01%