

FP CH 0-0,2 mm

980 - 1050 °C



Red earthenware body fine grog 0-0,2 mm
 Excelent drying behavior. Perfect glaze and underglaze behavior.
 Perfect for the artistic pottery, decorative, garden pots and sculpture.
 Very plastic and easy to work.
 Ideal for modelling

Technical data sheet

Drying			Firing		
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	5,50%	950°C	8,60%	12,79%	0,20%

Thermal coefficient

64.62x10⁻⁷°C⁻¹ (48.1-500°C)