

FB CH 0-0,5 mm

980 - 1020 °C



Black manganese body with grog 0-0,5 mm
Excellent drying behavior glazes and underglazes (slipware). Intended for artistic, decorative, and table ceramics. High plasticity, shapable and easy to work with. Ideal for turning and modeling.

Technical data sheet

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	6,00%	1000	8,00%	12,70%	0,80%

Thermal coefficient

77.3x10-7°C-1 (48.1-500°C)