

REFRAC

950 - 980 °C



Ferruginous paste with allow coefficient of expansión. Perfect for casseroles, baking trains and tajins. Smooth texture, special for direct flame.

Technical data sheet

Drying			Firing		
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
23%	8,00%	950	5,31%	12,80%	1,42%

Thermal coefficient

40.0x10⁻⁷°C⁻¹ (25-500°C)